

2021/02/10

List of Analyses

Time of Analysis: 02:26:17 PM

Sample No BMR 3

Program Fe100Ni

	Ag	Al	As	B	Ba	Be	BG	Bi	C	Ca	Cd
	%	%	%	%	%	%	%	%	%	%	%
Sample	0.00000	0.0286	0.0124	<0.0010	0.00000	0.00000	0.00000	0.0121	0.0368	0.00000	0.00000
	Ce	Co	Cr	Cu	Fe	Ga	In	La	Li	Mg	Mn
	%	%	%	%	%	%	%	%	%	%	%
Sample	0.00599	<0.0050	0.0397	0.0174	97.9	0.00000	0.00000	0.00204	0.00000	0.00508	1.68
	Mo	N	Na	Nb	Ni	P	Pb	S	Sb	Se	Si
	%	%	%	%	%	%	%	%	%	%	%
Sample	<0.0100	0.0377	0.00000	0.0485	0.0142	0.0170	<0.0100	0.0115	0.0115	0.00694	0.0313
	Sn	Sr	Ta	Te	Ti	V	W	Zn	Zr		
	%	%	%	%	%	%	%	%	%		
Sample	<0.0050	0.00000	<0.0300	0.00000	0.0183	<0.0050	<0.0100	<0.0020	0.00285		

2021/02/10

Time of Analysis: 02:35:32 PM

Sample No BMR 4

Program Fe100Ni

	Ag	Al	As	B	Ba	Be	BG	Bi	C	Ca	Cd
	%	%	%	%	%	%	%	%	%	%	%
Sample	0.00000	0.0357	0.0133	<0.0010	0.00000	0.00000	0.00000	0.0113	0.0538	0.00000	0.00000
	Ce	Co	Cr	Cu	Fe	Ga	In	La	Li	Mg	Mn
	%	%	%	%	%	%	%	%	%	%	%
Sample	0.00577	<0.0050	0.0344	0.0193	97.9	0.00000	0.00000	<0.0020	0.00000	<0.0050	1.40
	Mo	N	Na	Nb	Ni	P	Pb	S	Sb	Se	Si
	%	%	%	%	%	%	%	%	%	%	%
Sample	<0.0100	0.0319	0.00000	0.0492	0.0107	0.0136	<0.0100	<0.0101	0.0129	0.00766	0.273
	Sn	Sr	Ta	Te	Ti	V	W	Zn	Zr		
	%	%	%	%	%	%	%	%	%		
Sample	<0.0050	0.00000	<0.0300	0.00000	0.0232	<0.0050	<0.0103	<0.0020	0.00284		